

Parco

5323-70 EPDM Seals

Need 70-Durometer NSF 61 EPDM O-rings?

Parco is committed to being the leading supplier of EPDM O-rings for NSF/ANSI Standard 61 (NSF 61). That standard sets limits for the amount of chemicals permitted to seep into drinking water. Parco's low-cost, general-purpose, peroxide-cured 5323-70 EPDM compound is certified to NSF 61.

We've doubled our inventory, cut our prices 15 percent, and reduced or minimum order to about \$5. So when you need peroxide-cured EPDM O-rings that meet NSF 61, you no longer have to check more than one source for available inventory and competitive prices. Make Parco your first choice for NSF 61 O-rings.

5323-70 Meets Your Needs

1. Outstanding Resistance to Compression Set

Parco seals made from peroxide-cured 5323-70 have excellent resistance to compression set. After testing 5323-70 for 22 hours at 257°F, it had a compression set of only 13 percent. At 13 percent, 5323-70 significantly outperforms similar sulfur cured EPDM compounds. 5323-70's excellent compression set allows it to better maintain its elastomeric properties and original thickness, preserving seal integrity.

2. Excellent Resistance to Chloraminated Water

Parco's peroxide-cured 5323-70 compound has superior resistance to volume swell in chloraminated water applications. After testing for 70 hours at 212°F in chloraminated water, 5323-70 seals experienced volume swell of one percent. That low volume swell makes seals made from peroxide-cured 5323-70 substantially better than similar sulfur-cured compounds. Parco recommends its 5323-70 compound for chloraminated or chlorinated applications such as faucets, hose bibs, and other residential plumbing fixtures.

3. Exceptional Prices

Parco's 5323-70 prices are the lowest in the industry. We work with the best suppliers, buy in large volumes, and sell in standard quantity bags. Those features allow us to provide you with 5323-70 O-rings at great prices.

Key Features

Parco's 5323-70 EPDM seals are ideal for use in chloraminated water applications. Key features include:

- NSF 61 Listed:**
 Parco 5323-70 seals are approved for materials used in drinking water service (listed for maximum exposure of seal material 1.3in²/liter of commercial hot water at 180°F; listing includes domestic hot and cold water).
- Outstanding resistance to compression set:**
 Parco 5323-70 peroxide-cured seals had a compression set of only 13 percent after 22 hours at 257°F.
- Excellent resistance to chloraminated water:**
 Parco 5323-70 seals had a volume swell of 1 percent after 70 hours at 212°F in chloraminated water.
- Wide range of service temperatures:**
 Parco 5323-70 seals are suitable for applications ranging from -50 to +250°F.

Chemical Resistance

| USE WITH | DO NOT USE WITH |
|--|---|
| Acetone Automotive Brake Fluid Skydrol Steam Water | Automatic Transmission Fluid Gasoline Military Aircraft Hydraulic Fluid |

Typical Values for Compound 5323-70 General-purpose 70-durometer, NSF 61 listed EPDM

| Section of Spec. | Physical Property | Requirement ¹ | Typical Value | ASTM ² Test Method |
|------------------|---|--------------------------|---------------|-------------------------------|
| Z1 | Original Properties | | | |
| | Hardness, Shore A | 70 ± 5 | 68 | D2240 |
| | Tensile strength, MPa (psi), min. | 14.0(2031) | 14.1(2038) | D412 |
| Z2 | Heat Aging 70 hours at 125°C (257°F) | | | D573 |
| | Hardness change, pts., Shore A, max. | 10 | 3 | |
| | Tensile strength change, pct., max. | -20 | -19 | |
| B35 | Compression Set, Plied pct. of original deflection, max. 22 hours at 125°C (257°F) | 70 | 13 | D395 Method B |
| | Ozone Resistance Exposure Method B | Pass | Pass | D1171 |
| | Fluid Aging, Water 70 hours at 100°C (212°F) Volume change, pct. | ±5 | 1 | D471 |
| F19 | Low Temperature Property Nonbrittle after 3 minutes -55°C | Pass | Pass | D2137 |
| G21 | Tear Resistance Die C, kN/m, min. | 26 | 28 | D624 |

¹Compound 5323-70 meets the requirements shown above for ASTM D2000 M4CA714 B35 B44 C32 EA14 F19 G21 Z1 Z2.
²ASTM is the acronym for the American Society for Testing and Materials. ³IRM is the acronym for Industry Reference Material.
 Source: Parco Test Report 8448A and R & D data.

⚠ This brochure is intended as a guideline and reference. Appropriate testing and validation by users having technical expertise is necessary for proper use of Parco products.

Parco

Parco, Inc., 1801 S. Archibald Ave., Ontario, California 91761
 909-947-2200 Fax 909-923-0288 parcoinc.com